

## StreetLam

### PRODUCT DESCRIPTION

PVC calendered self-adhesive highly structured anti-slip laminating film.

**Face Material:** 385 µm clear satin PVC

**Adhesive:** Solvent acrylic permanent transparent

**Liner:** PE coated 135 g/sqm

### TYPICAL USE

Laminating film especially designed for short term outdoor applications on flat and slightly curved surfaces in combination with StreetRap printing media in order to:

- retard colour fade and protect printing media against UV radiation and abrasion
- enhance colours of the prints
- provides high anti-slip properties thanks to the abrasive particles bonded onto the PVC film
- has a high tack adhesive
- does not influence the pH level of substrate to which it is applied

Suitable for outdoor floorgraphics such as parking spaces, exhibitions and footpaths on concrete pavement and bitumen .

### PROCESSING

Specifically designed for media printed with solvent, eco-solvent & latex inks.

StreetLam must be kept clean and dry to achieve optimal anti-slip properties.

For specific settings of the laminator, please consult the technical manual that comes with the laminator from the original supplier.

Cleaning the laminator rollers with a lint-free cloth is required to remove abrasive dust particles that may detach from the film surface after lamination.

The printed media should be perfectly dry prior to lamination and be left to dry for at least 24h.

The use of industrial cleaning machines, cleaning chemicals or mechanical cleaners may deteriorate the overall performance of the film.

Due to the thickness of the film, delamination may occur if the overlaminated media is rolled too tight.

Mactac Laminating media must be applied following the instructions in TB 4.1 "Guidelines on handling, converting and applying Mactac Digital media", available from the resource section at [www.mactacgraphics.eu](http://www.mactacgraphics.eu).

### SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

### PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values    Test Method

Average Values    Test Method		
<b>Thickness</b>		
Face (microns)	385 µm	ISO 534
<b>Adhesive data, 23°C (N/25 mm)</b>		
Peel adhesion on glass		
- Quick tack	15	FTM9
- 24 hour residence	18	FTM1
<b>Dimensional stability</b>		
Shrinkage (48 hours at 70°C applied on Aluminium)	Max. 0.75 mm	FTM14
<b>Temperature ranges</b>		
Minimum application temperature (°C)	+ 15°C	
Service temperature range (°C)	- 30°C to + 70°C	
<b>Certifications</b>		
Fire Classification	Bfl-s1	EN13501-1
Slip Resistance*	R12	DIN51130

\* For more information on Slip Resistance, refer to "TB 4.7 - Guidelines of Anti-slip resistance Certification Digital Mactac".

### EXPECTED DURABILITY

#### Central Europe Zone 1

Unprocessed	Up to 6 months	ISO 4892-2
-------------	----------------	------------

\*For more information, refer to "TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films".

Note : Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure.

*DISCLAIMER*

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.